



# 50/50 CREAM CEMENT

## PRODUCT DESCRIPTION

Swan Cement produces 50/50 Cream Cement, a Masonry Binary Cement M3, conforming to Australian Standard AS 1316.

50/50 Cream Cement is manufactured to exacting standards at our Kwinana Works in Kwinana, Western Australia, for use in the construction and building industry and in domestic applications.

## SUPPLY

50/50 Cream Cement is available in 17.85 kg bags from the Kwinana Works and Customer Service Centres in regional areas.

## SPECIFICATION

50/50 Cream Cement exceeds the minimum specification for Masonry Binary Cement M3 given in AS 1316 and when mixed with the appropriate sand, is capable of producing mortar type M3 as defined in AS 3700.

50/50 Cream Cement is manufactured under a third party certified manufacturing and supply quality assurance system to ISO 9001 (BSI Certification No FS 604665).

50/50 Cream Cement is produced from Portland cement clinker, hydrated lime, and gypsum.

## APPLICATIONS

50/50 Cream Cement is ideal for internal or external mortars, and under-render finish.

## RENDER GUIDE

Use	Substrate	Mix ratio (volume)	
		Cement	Sand
Float/base coat	Clay brick	1	3.5
	Concrete block	1	3
Sand finish base coat	Clay brick	1	2.25
Sand finish top coat	S/F base coat	1	2.5

## MORTAR GUIDE

Mix	Mix ratio (volume)	
M3	Walls between 1 km and 10 km of a surf coastline or between 100 m and 1 km of a non-surf coastline, e.g. estuary and coastal river zones.  Walls in contact with fresh water or the ground in non-aggressive soils.  Internal walls subject to non-saline wetting and drying.	
Mix design – parts by volume		
Mix	Cement	Brickies sand
M3	1	3

\* Any admixtures used should be in accordance with the manufacturers instructions.

\*\* 50/50 Cream Cement contains an air-entraining agent, additional air entrainment is not required.

\*\*\* Please refer to AS 3700 – Masonry Structures for detailed information.

## TYPICAL PROPERTIES

### Physical Properties

Test	Typical Values	AS 1316 Requirement
Setting Time (hr:min) AS 2350.4		
Initial	1:30	Min 0:75
Final	2:20	Max 12:00
Soundness (%) AS 2350.17		
	< 0.1	Max 1
Water Retention (%) AS 2350.17		
	80	Min 70
Air content (%) AS 2350.16		
	19.5	10-25
Compressive Strength ISO-CEN mortar bars (MPa) AS 2350.11		
7 Day	22 - 34	Min 3.5
28 Day	25 - 40	Min 6

### Chemical Properties

Test	Units	Typical Values
Sulphur Trioxide	%	2.7
Loss on Ignition	%	6.8 – 8.8
Chloride	%	0.01
Equivalent Alkalis	%	0.5
Hexavalent Chromium	mg/kg	Trace
Crystalline Silica	%	Trace
Components		
Portland Clinker	%	70 – 80
Gypsum	%	5 - 7
Hydrated Lime	%	20 – 30

**50/50 CREAM CEMENT****SAFETY INFORMATION**

For safety information refer to the Safety Data Sheet for 50/50 Cream Cement.

**HANDLING AND STORAGE**

Manual handling of bag products without due care and attention may result in personal injury. Unless you have been trained in manual handling methods it is suggested that you share the load with another person.

50/50 Cream Cement can be kept for up to six months provided it is stored in a place, off the ground, protected from ingress of moisture. Ingress of moisture can occur due to rain, liquid spillage (on or around the product) or a high humidity climate. Such exposure will degrade the

performance of the product.

**CONTACT POINTS**

**For further information contact the Sales and Marketing Department at:**

Swan Cement Ltd  
ABN 50 008 673 470  
Lot 242 Russell Road East  
Munster WA 6166

**Telephone:** 08 9411 1111

**Facsimile:** 08 9411 1120

**Email:** [sales@cockburncement.com.au](mailto:sales@cockburncement.com.au)

**Web Site:** [www.swacement.com.au](http://www.swacement.com.au)

**DISCLAIMER**

While the information in this Product Data Sheet has been prepared in good faith, Swan Cement Limited does not warrant that the information is accurate, complete or up to date.

Each user of any information, or any product referred to, in this Product Data Sheet must:

- Determine whether the information or product is suitable for their purpose;
- Assess and control any risks associated with the information or product; and
- Obtain professional advice in relation to the use of the information or product.

Failure to do so may result in serious damage or injury.

To the extent permitted by law, Swan Cement Limited:

- Excludes all representations, warranties and guarantees in relation to any information in this Product Data Sheet; and
- Will not be liable for any direct, indirect, consequential, incidental, special or economic loss (including but not limited to any loss of actual or anticipated profits, revenue, savings, production, business, opportunity, access to markets, goodwill, reputation, publicity, or use) arising from any use of or reliance on any information in this Product Data Sheet.

The Swan Cement logo and Swan Cement are registered trademarks of Swan Cement Limited and its related entities.