



ABN 50 006 673 470

Cement Test Certificate

Final

Lot 242 Russell Road East,
Munster WA 6166
PO Box 38, Hamilton Hill WA 6963
T: +61 8 9411 1000
F: +61 8 9411 1150
www.cockburncement.com.au

Product Certified: Type HE High Early Strength Cement (Creme)
Test Certificate Number: 180602
Produced At: Cockburn Cement, Kwinana Plant, WA
Sample Code: B0641d3
Sample Date: 22/05/2018

Nominal Blend	Requirements	Result
Clinker		>86.5 %
Ground Granulated Iron Blast-Furnace Slag		Nil
Mineral Addition	Max 7.5 %	<5 %
Calcium Sulphate		<5 %
Minor Additional Constituents	Max 5 %	Nil

Reportable Property	Test Method	Requirements of AS3972	Result
3 Day Strength	AS2350.11	Min 25.0 MPa	37.7 MPa
7 Day Strength	AS2350.11	Min 40.0 MPa	52.5 MPa
28 Day Strength	AS2350.11	N/R	62.2 MPa
Initial Set Time	AS2350.4	Min 45 min	75 min
Final Set Time	AS2350.4	Max 360 min	165 min
Soundness	AS2350.5	Max 5 mm	1 mm
Sulfuric Anhydride content (SO ₃)	AS2350.2	Max 3.5 %	3.2 %
Chloride Ion	BH-TM-0507	Max 0.10 %	0.009 %

Other Properties			
SiO ₂	AS2350.2	N/R	21.8 %
Al ₂ O ₃	AS2350.2	N/R	3.7 %
Fe ₂ O ₃	AS2350.2	N/R	0.4 %
CaO	AS2350.2	N/R	64.7 %
MgO	AS2350.2	N/R	1.0 %
Na ₂ O Equivalent	AS2350.2	N/R	0.6 %
Loss on Ignition	AS2350.2	N/R	4.4 %
Fineness Index	AS2350.8	N/R	415 m ² /kg
Normal Consistency	AS2350.3	N/R	27.8 %
Brightness (L)*	MU-TM-2614	N/R	88

This document shall not be reproduced except in full.

REMARKS

These test result apply specifically to the sample as received at the Adelaide Brighton Cement Birkenhead Laboratory (Accreditation number: 252), 62 Elder Rd Birkenhead SA 5015.

This despatch grab sample complies to the requirements of AS3972:2010, Type HE Cement.

*NATA accreditation 252 does not cover the performance of this service.

N/R = No Requirement



Accredited for compliance with ISO/IEC 17025 - Testing. The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards.

Approved Signatory

M. Wythe

Issue Date: 5/07/2018