



an ADBRI company
ABN 50 006 673 470

Cement Test Certificate

Final

Lot 242 Russell Road East,
Munster WA 6166
PO Box 38, Hamilton Hill WA 6963
T: +61 8 9411 1000
F: +61 8 9411 1150
www.cockburncement.com.au

Product Certified: Type HE High Early Strength Cement (White)
Test Certificate Number: 240283
Customer: Cockburn Cement, Kwinana Plant, WA
Sample Code: B0a87af
Sample Date: 04/04/2024

Nominal Blend	Requirements	Result
Clinker		>85 %
Ground Granulated Iron Blast-Furnace Slag		Nil
Mineral Addition	Max 7.5 %	<7.5 %
Calcium Sulphate		4-8 %
Minor Additional Constituents	Max 5 %	<5%

Reportable Property	Test Method	Requirements of AS3972	Result
3 Day Strength	AS/NZS2350.11	Min 25.0 MPa	38.4 MPa
7 Day Strength	AS/NZS2350.11	Min 40.0 MPa	49.1 MPa
28 Day Strength	AS/NZS2350.11	N/R	58.9 MPa
Initial Set Time	AS/NZS2350.4	Min 45 min	105 min
Final Set Time	AS/NZS2350.4	Max 360 min	165 min
Soundness	AS/NZS2350.5	Max 5 mm	1 mm
Sulfuric Anhydride content (SO ₃)	AS2350.2	Max 3.5 %	3.1 %
Chloride Ion	BH-TM-0507	Max 0.10 %	0.020 %

Other Properties

SiO ₂	AS2350.2	N/R	21.7 %
Al ₂ O ₃	AS2350.2	N/R	3.7 %
Fe ₂ O ₃	AS2350.2	N/R	0.2 %
CaO	AS2350.2	N/R	64.8 %
MgO	AS2350.2	N/R	1.6 %
Na ₂ O Equivalent	AS2350.2	N/R	0.5 %
Loss on Ignition	AS2350.2	N/R	4.2 %
Fineness Index	AS/NZS2350.8	N/R	420 m ² /kg
Normal Consistency	AS/NZS2350.3	N/R	29.7 %
Brightness (L)*	MU-TM-2614	N/R	91

This document shall not be reproduced except in full.

REMARKS

These test result apply specifically to the sample as received at the Adbri Cement Birkenhead Laboratory (Accreditation number: 252), 62 Elder Rd Birkenhead SA 5015.

This despatch grab sample complies to the requirements of AS3972:2010, Type HE Cement.

*NATA accreditation 252 does not cover the performance of this service.

N/R = No Requirement



Accredited for compliance with ISO/IEC
17025 - Testing.

M. Wythe

Approved Signatory

M. Wythe

Issue Date: 01/06/2024